

نجيله صناعة اندونيسيا بني



Technical Data

| PRODUCT SPECIFICATION | | | |
|---|----------------------------------|--|------------------|
| Product name: | Brown Indonesia | Application: | Landscape |
| Model: | Brown Indonesia | Roll width: | 4.0m/2.0m |
| Color: | Fern Cyan& Fern Green | Roll length: | On request |
| YARN CHARACTERISTICS | | | |
| Yarn 1 | | Yarn 2 | |
| Structure: | Monofilament | Structure: | Monofilament |
| Composition: | PE | Composition: | PP |
| Dtex: | 3400 | Dtex: | 2200 |
| Tape thickness: | 55~75µm | Tape thickness: | N/A |
| Tape width: | 0.65-0.85mm | Tape width: | N/A |
| UV Effects (ENISO 20105) | Grey Scale 4-5, no visual Change | Yarn Breaking Strength (ASTM D2256) | ≥ 110 N |
| Pile Burn Test:(ASTM D2859) | Pass | Yarn Melt Point: (ASTM D789) | 120°C |
| CARPET CHARACTERISTICS | | | |
| TURF | | | |
| Pile height: | 40mm±1mm | Gauge: | 3/8inch |
| Number of strands per tuft: | 14 strands | Stitches per 10cm: | 16±1 |
| Stitches per m² | 16800±100 | Total yarn weight: | 838.56g/sqm ±10% |
| BACKING | | | |
| Primary backing: | PP + mesh scrim inlay | | |
| Weight: | 150g/sqm | | |
| Secondary backing: | Latex | | |
| Weight: | 950g /sqm ±10% | | |
| Total carpet weight: | 1938.56g/sqm ±100g/sqm | | |
| Carpet | | | |
| Carpet tuft withdrawal: (EN 13744 & ISO4919) | ≥ 30N | Water permeability of carpet: (EN12616) | ≥ 2000mm/h |

